



BOSCOSEAL TORCH ON

FULLY BONDED TORCH-ON APPLIED WATERPROOFING MEMBRANE

KEY FEATURES

Plastoelastomeric modified bitumen

- Good UV resistance (Mineral Finish)
- Good elasticity and durable
- Resistant to atmospheric pollutants and chemical environment

Spunbond polyester reinforcement

- Gives mechanical strength
- Accomodates thermal stress
- Provides dimensional stability

Sanded or Mineral chip finish

- Minimise UV heat and radiation
- Prolong life of membrane

DESCRIPTION

Boscoseal Torch On is a fully-bonded plastoelastomeric modified bitumen waterproofing membrane consisting of visco-elastic resins and inert filler, reinforced with spunbond polyester carrier.

Type:

- Boscoseal Torch On 3P - Sanded Finish (3mm)
- Boscoseal Torch On 4P - Sanded Finish (4mm)

- Boscoseal Torch On 3P - Mineral Finish (4kg/m²)
- Boscoseal Torch On 4P - Mineral Finish (4.5kg/m²)

RECOMMENDED USES

- Trafficable roof
- Non-trafficable roof
- Roof garden
- Inverted Roof
- Plaza decks
- Landscape areas
- Roof refurbishment

SUBSTRATE TYPES

Bond well to:

- Concrete
- Cement sand backings
- Steel deck
- Metal deck
- PVC pipes
- Old stable finishes

SURFACE PREPARATION

On new roof installation, the floor screed shall be done at a recommended slope ranging from 1 to 5% between 25 to 50 mm thickness to achieve gradient and crossfalls.

Existing roof systems shall be thoroughly inspected and prepared to provide a structural sound, smooth, dry substrate for the attachment of Boscoseal Torch On membrane.

Areas where the membrane is to be installed must be clean, dry, smooth and treated with a coat of Bostik Bituminous Primer to provide good bonding between the membrane and the substrate.

APPLICATION INSTRUCTION

PRIMING

Before installation, prime substrate with Bostik Bitumen Primer at the rate of 5m² per liter depend on substrate condition

PLACING

Starting from the lowest point where the drainage outlet is positioned, unrolled the Boscoseal Torch On membrane from its original packaging and placed on the correct position where it will be torched later.

The membrane is then re-rolled without changing its original alignment. Slowly unrolled again and whilst unrolling, heat up the burn-off film on the underside of the membrane by a propane gas torch at controlled temperature causing surface changes and subsequent adhesion to the substrate. All overlaps, edges end and seams must be overlap by at least 75 to 100mm and shall be formed to shed water.

The bitumen compound coming out from the lightly pressed heated overlap of the membrane should be carefully leveled by spreading it on the lap with a heated round trowel to form a sealing bead.

PACKAGING

1m width x 10m length per roll

STORAGE AND SHELF LIFE

Store Boscoseal Torch On in vertical position at temperature between 5°C and 30°C in cover and dry place out of direct sun light.

PERFORMANCE PROPERTIES

Characteristic	Test Method	Sanded Membrane		Mineral Membrane	
		3mm	4mm	4 kg	4.5kg
Watertightness	EN 928:2000 Method A	Pass	Pass	Pass	Pass
External fire performance	EN 13501-5	Class F Roof	Class F Roof	Class F Roof	Class F Roof
Reaction to fire	EN 13501-1	Class F	Class F	Class F	Class F
Ultimate Tensile Strength Resistance at break : Longitudinal Transverse	EN 12311-1	500N/50mm 400N/50mm	500N/50mm 400N/50mm	400N/50mm 300N/50mm	400N/50mm 300N/50mm
Ultimate Tensile Strength Elongation at break : Longitudinal Transverse	EN 12311-1	35% 35%	35% 35%	35% 35%	35% 35%
Resistance to tearing Longitudinal Transverse	EN 12310-1	130N 130N	130N 130N	130N 130N	130N 130N
Resistance to impact	EN 12691/A	800mm	800mm	700mm	700mm
Resistance to static loading	EN 12730-1/B	10kg	10kg	10kg	10kg
Flexibility at low temperature	EN 1109	0°C	0°C	0°C	0°C
Creeping at heat	EN 1110	100°C	100°C	100°C	100°C
Dimensional Stability	EN 1107-1	± 0.3%	± 0.3%	± 0.3%	± 0.3%
Water vapour transmission	EN 1931	20,000µ	20,000µ	20,000µ	20,000µ
Shear resistance of joints	EN 12317-1	400/300N per 50mm	400/300N per 50mm	300/200N per 50mm	300/200N per 50mm

HEALTH AND SAFETY

Suitable protection clothing, gloves and eye protection should be worn. For more detailed information, refer to Material Safety Data Sheet.

LIMITED WARRANTY

The information and recommendations relating to the application and end-use of the product are given in good faith and based on tests which we believe to be reliable. However, no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship, whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. No guarantee of their accuracy can be made because of the great range of field conditions and variation encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with limited warranty only, and on condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik be liable to anyone except for replacement of the products or refund of the purchase price.

BOSTIK HOTLINE

Smart help
+606 678 9788



Bostik Findley (Malaysia) Sdn. Bhd. (286152V)

Lot 112 & 113, Kawasan Perindustrian Senawang,
70450 Seremban, Negeri Sembilan,
Malaysia

Tel: +606 678 9788 Fax: +606 678 9766

www.bostik.com

Singapore Branch (T12FC0033E)

2, Jurong East Street 21#02-184, IMM Building
Singapore 609601

Tel: +65 6863 4088 Fax: +65 6863 4077

www.bostik.com.sg

This document supersedes all previously published literature.